

Emblemas Digiline

Los emblemas están impresos digitalmente. Se puede pedir cualquier color deseado comparando con la gama Pantone. Una ventaja adicional del Digiline es el período de entrega relativamente corto de 7 días después de la aprobación del diseño gráfico.

El Digiline está disponible en tres versiones: **Digiline**, **Digiline Sports** y **Digiline Low Melt**.

Digiline

Los emblemas Digiline se pueden aplicar a materiales donde se necesitan resistencia y durabilidad. El emblema es resistente al lavado industrial a 95 ° C. A pesar de esta alta temperatura de lavado, los colores frescos, brillantes y vibrantes están garantizados durante mucho tiempo. El Digiline se puede producir con un efecto de bordado, que realza su aspecto.

Los emblemas Digiline se aplican al tejido a una temperatura de 195 ° C. El proceso de producción y los emblemas Digiline están certificados por Oeko-Tex.

Digiline Sports & Digiline Low Melt

Digiline Sports y Digiline Low Melt son más ligeros y flexibles en comparación con el Digiline estándar. Estos emblemas son adecuados para fines promocionales y ropa deportiva. El nombre del club, el logotipo o el patrocinador se presentan de la mejor manera posible con la versión Sports y Low Melt. Además de las imágenes a todo color, para Digiline Sports y Digiline Low Melt son posibles efectos como 3D, relieve, brillo e incluso una apariencia de cuero.

Digiline Sports se aplica sobre tejidos a una temperatura de 145°C, Digiline Low Melt a una temperatura de 130°C. Ambos se pueden lavar hasta 40°C. Estos emblemas se aplican con las máquina termoselladoras Thermopatch. Alternativamente, para aumentar la facilidad de uso, Digiline Sports y Digiline Low Melt también son fáciles de aplicar con plancha sobre cualquier tipo de tejido. El proceso de producción y los emblemas Digiline Sports y Digiline Low Melt cuentan con la certificación Oeko-Tex.

Cantidades

La cantidad mínima de pedido es de 15 piezas por diseño.

Digiline

Digiline				
Digiline Sports				

Digiline Low Melt



Digiline emblems are compliant to Oekotex product class II, under certificate number 1012046 Centexbel.

Application

Digitally printed emblems which are applied to textiles or other heat sealable materials by heat and pressure for decoration or identification.

Properties

- Digiline is washable up to 95°C.
- Good chemical resistance.
- Digiline Sports and Digiline Low Melt are washable up to 40 °C
- Digiline products are suitable for all textiles which allow the thermoplastic adhesive to penetrate and bind itself to it and which are resistant to its application temperatures.

Limitations of use

Digiline with high temperature glue applications are washable up to 95 °C industrial washing. Digiline Sports and Digiline Low Melt with low temperature glue application are washable up to 40 °C.

Physical properties

Color imprint: various

Color base textile: white

Color glue laminate: clear

Sizes: various

Before sealing

Ensure that the to be marked textile is free of lint, dust, dirt and no seams, zipper, buttons etc. are near the place where the heat sealing will be performed.

Remark:

- Good bonding can be prevented in pre-conditioned fabrics with a dirt or water repellent or flame retardant treatment or coating.
- Pre-sealing can amend problems with adhesion on certain repellent or flameretardant coated textiles.
- Re-sealing can amend problems with adhesion on certain repellent or flameretardant treated textiles.

Heat seal instructions

- Digiline: 195 °C for 14 seconds at 0.5 kg/cm2* pressure on a pneumatic heat seal machine, or firm - strong pressure on a manually operated machine.

- Digiline Sports: 145 °C for 15 seconds at 0.5 kg/cm2* pressure, or medium pressure on a manually operated machine.
- Digiline Low Melt: 130 °C for 15 seconds at 0.5 kg/cm2* pressure, or medium pressure on a manually operated machine.
- Make sure that the sealing plate of the machine is clean and undamaged.
- Close the heat seal press with the set temperature, time and pressure.
- Remove the garment from the machine after the heat sealing cycle is finished.
- Place the next article and repeat above.

(*) For an optimal heat sealing result we advise to set the pressure on any large platen pneumatic heat seal press to 3-5 bar on the pressure regulator of the machine, when using the standard issued underplaten. When using smaller underplatens, decrease pressure to avoid damage to the transfers.

Handling and storage

Keep away from oxidizing agents, from strongly alkaline en strongly acid materials. Store out of direct sunlight, in a cool and dry place.

Scroll down for Digiline Sports and Digiline Low Melt

Digiline emblems (up to 95 °C laundry wash)			
Type of fabric	Temp. °C	Pressing time in sec.	Pressure in Bar Low/Medium/High
Fleece, 100% Polyester	195 - 204	15	4-6 (Medium/High)
Polyurethane or PVC coated polyester (rainwear), cover with baking paper	195 - 204 Repress	15 15	4.5 (Medium/High)
Knitted fabrics, 100% polyester, viscose, acrylic (Sportswear, light workwear)	-	-	-
Knitted fabrics, 100% wool, cotton (Sportswear, light workwear)	-	-	-
Knitted fabrics, cotton or polyester with elastane 98%/2%	-	-	-

Flame-retardant cotton or polyester cotton (FR treated, Proban®)	195 – 204	15 – 12	4.5 (Medium/High)
Cotton/polyamide 55%/45%	Preheat 195 – 204	10 15 – 12	4.5 (Medium/High)
Cotton/polyester 65%/35% or 60%/40% (with DWR finish)*	195 – 204	12	4.5 (Medium/High)
Aramid/Viscose 50%/50%	195 – 204	12	4.5 (Medium/High)
Linen, 100%	195 – 204	20	4.5 (Medium/High)
Aramid (Nomex III), 100%	195 – 204	12	4.5 (Medium/High)
Polyamide (Nylon), 100% (with DWR finish)*	195 – 204	12	4.5 (Medium/High)
Polyester 100% (with DWR finish)*	195 – 204	12	4.5 (Medium/High)
Polyester Cleanroom material anti-static 99%/1%	195 – 204	12	4.5 (Medium/High)

Digiline Sports (low to medium temperature, digital emblems, sportswear, light workwear, up to 40 °C industrial wash)			
Type of fabric	Temp. °C	Pressing time in sec.	Pressure in Bar Low/Medium/High
Fleece, 100% Polyester	140	15	3 (Low)
Polyurethane or PVC coated polyester (rainwear), cover with baking paper	140	15	3 (Low)

Knitted fabrics, 100% polyester, viscose, acrylic (Sportswear, light workwear)	130 - 140	15	3 (Low)
Knitted fabrics, 100% wool, cotton (Sportswear, light workwear)	140	15	3 (Low)
Knitted fabrics, cotton or polyester with elastane 98%/2%	130 - 140	15	3 (Low)
Flame-retardant cotton or polyester cotton (FR treated, Proban®)	-	-	-
Cotton/polyamide 55%/45%	140	15	3 (Low)
Cotton/polyester 65%/35% or 60%/40% (with DWR finish)*	140	15	3 (Low)
Aramid/Viscose 50%/50%	-	-	-
Linen, 100%	140	15	3 (Low)
Aramid (Nomex III), 100%	-	-	3 (Low)
Polyamide (Nylon), 100% (with DWR finish)*	-	-	3 (Low)
Polyester 100% (with DWR finish)*	-	-	3 (Low)
Polyester Cleanroom material anti-static 99%/1%	-	-	-

Digiline Low Melt (low temperature, digital emblems, sportswear, light workwear, up to 40 °C home wash)

Type of fabric	Temp. °C	Pressing time in sec.	Pressure in Bar Low/Medium/High
Fleece, 100% Polyester	130	15	3 (Low)
Polyurethane or PVC coated polyester (rainwear), cover with baking paper	130	15	3 (Low)
Knitted fabrics, 100% polyester, viscose, acrylic (Sportswear, light workwear)	130	15	3 (Low)
Knitted fabrics, 100% wool, cotton (Sportswear, light workwear)	130	15	3 (Low)
Knitted fabrics, cotton or polyester with elastane 98%/2%	130 - 140	15	3 (Low)
Flame-retardant cotton or polyester cotton (FR treated, Proban®)	-	-	-
Cotton/polyamide 55%/45%	140	15	3 (Low)
Cotton/polyester 65%/35% or 60%/40% (with DWR finish)*	-	-	-
Aramid/Viscose 50%/50%	-	-	-
Linen, 100%	130	15	-
Aramid (Nomex III), 100%	-	-	-
Polyamide (Nylon), 100% (with DWR finish)*	-	-	-

Polyester 100% (with DWR finish)*	-	-	-
Polyester Cleanroom material anti-static 99%/1%	-	-	-

**DWR finish: Durable Water Repellent finish, meaning a water (dirt, oil) repellent coating on textiles based on silicone, nanotechnology, wax, and fluorocarbon.*
FR: Flame Retardant

Disclaimer

No rights can be derived from the instructions or data provided online. The information is intended for general guidance only and is subject to change without notice. We do not guarantee the accuracy, completeness, or reliability of the information provided. Users are advised to verify any information before acting on it. We accept no liability for any damage incurred because of relying on this information.