

Lángálló FR

Jelölje munkaruháját a Thermopatch megbízható, lángálló megoldásaival, amelyeket a maximális védelem és tartósság érdekében terveztek.

Ready FR & ReadyPly FR

A Thermopatch által kifejlesztett Ready FR és ReadyPly FR emblémák hőállóak, és ideálisak lángálló munkaruházatra való rögzítésre. A ReadyPly FR öntapadó réteggel rendelkezik a könnyebb elhelyezés érdekében, és mindkét opció szinte bármilyen formában vagy színben testreszabható, valamint teljes mértékben megfelel az EN 469 szabványnak. A Ready termékekről további információért kattintson [ide](#).

Truflex FR

A Truflex FR népszerű Truflex transzferünk lángálló változata, amely fokozott biztonságot kínál a külön ehhez a felhasználáshoz adaptált ragasztóval és gyártási folyamattal. Független teszteléssel tanúsított, akár 60 °C-os mosást is kibír, és szinte bármilyen PMS színben részletes, jól látható ábrákat jelenít meg. 25 darabos minimális rendelési mennyiségben kapható. A Truflex termékekről további információért kattintson [ide](#).

Az ezen az oldalon található kék „Tanúsítványok” fülön található vizsgálati jelentés több mint tíz különböző típusú textíliával készült.

Textra FR

A Textra FR megbízható választás azon szervezetek számára, amelyek lángálló, kiváló minőségű és esztétikus megjelenésű nyomatot szeretnének munkaruházatra alkalmazni. Ez a speciálisan kifejlesztett transzfer megfelel a védőruházatra vonatkozó szigorú előírásoknak, anélkül hogy kompromisszumot kellene kötni a megjelenés vagy a részletgazdagság terén. A Textra FR tartós megoldást kínál, amely ellenáll a megterhelő munkakörülményeknek, és kiválóan rögzül műszaki textíliákon. A full-colour nyomat mély színeket és éles kontúrokat biztosít – így a biztonság és a professzionális megjelenés tökéletes összhangba kerülnek. A Textra termékekről további információért kattintson [ide](#).

HiQ FR

A HiQ FR a legjobb választás azokhoz a munkaruhákhoz, ahol a lángálló tulajdonságok kulcsfontosságúak. A szigorú ISO szabványoknak (EN ISO 11611: 2015 és EN ISO 11612: 2015) megfelelő változat folyamatos szalagtekercs vagy perforált címke formájában kapható, így kiváló eredményt biztosít magas igényeket támasztó körülmények között is. A HiQ termékekről további információért kattintson [ide](#).

Reflektív szalag

Javítsa a láthatóságot és a biztonságot gyenge fényviszonyok között a Thermopatch fényvisszaverő szalagjával. Két méretben kapható fényvisszaverő, lángálló szalagunk megfelel a fokozott védelmet és láthatóságot igénylő munkaruhák igényeinek. A fényvisszaverő szalagról további információért kattintson [ide](#).

Plotter transzferek FR

A Thermopatch ezüst színben gyártott plotter transzferjei ideálisak gyenge fényviszonyokkal rendelkező munkakörnyezetben. Ezek a fényvisszaverő, lángálló transzferek megfelelnek az EN ISO 20471 szabványnak, és tökéletesek az extra biztonsági intézkedéseket igénylő egyenruhákhoz. A fényvisszaverő emblémákról és a Plotter transzferekről további információért kattintson [ide](#).

Ready FR	15-12 seconds	195-204 °C	Pressure 0.5 kg / cm ²	95
ReadyPly FR	17-14 seconds	195-204 °C	Pressure 0.5 kg / cm ²	95

For more detailed press instructions for Ready and ReadyPly FR on various fabrics, click [here](#).

Truflex FR	12-15 seconds	Hot Peel	185-160 °C	Pressure 0.5 kg / cm ²	60
------------	---------------	----------	------------	-----------------------------------	----

For more detailed press instructions for Truflex on various fabrics, click [here](#).

HiQ-FR	20 seconds	204 °C	Pressure 0.5 kg / cm ²	60
--------	------------	--------	-----------------------------------	----

Reflective tape	15-10 seconds	150-190 °C	Pressure 0.5 kg / cm ²	60
-----------------	---------------	------------	-----------------------------------	----

Plotter transfers FR	15-12 seconds	Cold Peel	150-165 °C	Pressure 0.5 kg / cm ²	60
----------------------	---------------	-----------	------------	-----------------------------------	----

Scroll down for other FR-products.

Ready FR emblems (up to 95 °C laundry wash)			
Type of fabric	Temp. °C	Pressing time in sec.	Pressure in Bar Low/Medium/High
Fleece, 100% Polyester	–	–	–

Polyurethane or PVC coated polyester (rainwear), cover with baking paper	-	-	-
Knitted fabrics, 100% polyester, viscose, acrylic (Sportswear, light workwear)	-	-	-
Knitted fabrics, 100% wool, cotton (Sportswear, light workwear)	185 – 195	15	4-5 (Medium/High)
Knitted fabrics, cotton or polyester with elastane 98%/2%	-	-	-
Flame-retardant cotton or polyester cotton (FR treated, Proban®)	185 – 195	15	4-6 (Medium/High)
Cotton/polyamide 55%/45%	Preheat 195	10 15	4-6 (Medium/High)
Cotton/polyester 65%/35% or 60%/40% (with DWR finish)*	195	15	4-6 (Medium/High)
Aramid/Viscose 50%/50%	185	15	4-6 (Medium/High)
Linen, 100%	195	15	4-6 (Medium/High)
Aramid (Nomex III), 100%	185	15	4-6 (Medium/High)
Polyamide (Nylon), 100% (with DWR finish)*	185	15	4-6 (Medium/High)
Polyester 100% (with DWR finish)*	185	15	4-6 (Medium/High)
Polyester Cleanroom material anti-static 99%/1%	-	-	-

ReadyPly FR emblems (up to 95 °C laundry wash)			
Type of fabric	Temp. °C	Pressing time in sec.	Pressure in Bar Low/Medium/High
Fleece, 100% Polyester	-	-	-
Polyurethane or PVC coated polyester (rainwear), cover with baking paper	-	-	-
Knitted fabrics, 100% polyester, viscose, acrylic (Sportswear, light workwear)	-	-	-
Knitted fabrics, 100% wool, cotton (Sportswear, light workwear)	185 - 195	15	4-5 (Medium/High)
Knitted fabrics, cotton or polyester with elastane 98%/2%	-	-	-
Flame-retardant cotton or polyester cotton (FR treated, Proban®)	185 - 195	15	4-6 (Medium/High)
Cotton/polyamide 55%/45%	Preheat 195	10 15	4-6 (Medium/High)
Cotton/polyester 65%/35% or 60%/40% (with DWR finish)*	195	15	4-6 (Medium/High)
Aramid/Viscose 50%/50%	185	15	4-6 (Medium/High)
Linen, 100%	195	15	4-6 (Medium/High)
Aramid (Nomex III), 100%	185	15	4-6 (Medium/High)

Polyamide (Nylon), 100% (with DWR finish)*	-	-	-
Polyester 100% (with DWR finish)*	-	-	-
Polyester Cleanroom material anti-static 99%/1%	-	-	-

**DWR finish: Durable Water Repellent finish, meaning a water (dirt, oil) repellent coating on textiles based on silicone, nanotechnology, wax, and fluorocarbon.*

FR: Flame Retardant

Disclaimer

No rights can be derived from the instructions or data provided online. The information is intended for general guidance only and is subject to change without notice. We do not guarantee the accuracy, completeness, or reliability of the information provided. Users are advised to verify any information before acting on it. We accept no liability for any damage incurred because of relying on this information.