

Alev Geciktirici

İş kıyafetlerinizi, Thermopatch'in maksimum koruma ve dayanıklılık için tasarlanmış güvenilir, alev geciktirici çözümleriyle güçlendirin.

Ready FR ve ReadyPly FR

Thermopatch tarafından özel olarak geliştirilen Ready FR ve ReadyPly FR armaları, ısıya dayanıklıdır ve alev geciktirici iş kıyafetlerinde kullanım için idealdir. ReadyPly FR, kolay konumlandırma için kendinden yapışkanlı bir katmana sahiptir ve her iki seçenek de neredeyse her şekil veya renkte özelleştirilebilir. Üstelik, EN 469 standartlarına tamamen uygundur. Ready ürünleri hakkında daha fazla bilgi için [buraya](#) tıklayın.

Truflex FR

Truflex FR, popüler Truflex transfer etiketimizin alev geciktirici versiyonudur ve geliştirilmiş yapışkan ve üretim süreciyle daha yüksek güvenlik sunar. Bağımsız olarak test edilmiş ve sertifikalandırılmış olan bu ürün, 60 °C'ye kadar yıkamaya dayanıklıdır ve neredeyse her PMS renginde detaylı ve reflektörlü tasarımları destekler. Minimum 25 adetlik siparişlerle temin edilebilir. Truflex ürünleri hakkında daha fazla bilgi için [buraya](#) tıklayın.

Ondan fazla farklı tekstil türünde hazırlanan test raporları için bu sayfadaki mavi "Sertifikalar" sekmesine göz atın.

Textra FR

Textra FR, iş kıyafetlerine alev geciktirici, yüksek kalitede ve görsel açıdan güçlü baskı uygulamak isteyen kuruluşlar için güvenilir bir tercihtir. Özel olarak geliştirilen transfer etiketi, görünüm veya detaydan ödün vermeksizin iş güvenliği kıyafetlerinin katı gereksinimlerini karşılar. Textra FR sayesinde, zorlu çalışma koşullarına dayanabilen ve teknik tekstil ürünlerine mükemmel bir şekilde yapışabilen dayanıklı bir transfer etiketi çözümüne sahip olursunuz. Tam renkli baskı, derin renkler ve keskin hatlar sunar, emniyet ve profesyonelliği aynı anda sunar. Textra ürünleri hakkında daha fazla bilgi için [buraya](#) tıklayın.

HiQ FR

HiQ FR, alev geciktirici özelliklerin kritik olduğu iş kıyafetleri için en ideal seçenektir. Yüksek ISO standartlarını (EN ISO 11611: 2015 ve EN ISO 11612: 2015) karşılayan bu seçenek, kesintisiz bant ruloları veya hazır kesim etiketler olarak sunulmakta ve zorlu koşullarda yüksek performans sağlamaktadır. HiQ ürünleri hakkında daha fazla bilgi için [buraya](#) tıklayın.

Reflektif Bant

Thermopatch'in reflektif bandı ile düşük ışık koşullarında fark edilebilirliği ve güvenliği artırın. İki farklı boyutta sunulan yansıtıcı ve alev geciktirici bandımız, ek koruma ve fark edilebilirlik gerektiren iş kıyafetlerinin gereksinimlerini karşılar. Reflektif bant hakkında daha fazla bilgi için [buraya](#) tıklayın.

Alev Geciktirici Ploter Transfer Etiketleri

Thermopatch'in gümüş renkli ploter transfer etiketleri, düşük ışık koşullarındaki çalışma ortamları için

idealdir. Bu reflektörlü ve alev geciktirici transfer etiketleri, EN ISO 20471 standartlarına uygundur ve ekstra güvenlik önlemlerine sahip olması gereken üniformalar için idealdir. Reflektörlü armalar ve ploter transfer etiketleri hakkında daha fazla bilgi için [buraya](#) tıklayın.

Ready FR	15-12 seconds	195-204 °C	Pressure 0.5 kg / cm ²	95
ReadyPly FR	17-14 seconds	195-204 °C	Pressure 0.5 kg / cm ²	95

For more detailed press instructions for Ready and ReadyPly FR on various fabrics, click [here](#).

Truflex FR	12-15 seconds	Hot Peel	185-160 °C	Pressure 0.5 kg / cm ²	60
------------	---------------	----------	------------	-----------------------------------	----

For more detailed press instructions for Truflex on various fabrics, click [here](#).

HiQ-FR	20 seconds	204 °C	Pressure 0.5 kg / cm ²	60
--------	------------	--------	-----------------------------------	----

Reflective tape	15-10 seconds	150-190 °C	Pressure 0.5 kg / cm ²	60
-----------------	---------------	------------	-----------------------------------	----

Plotter transfers FR	15-12 seconds	Cold Peel	150-165 °C	Pressure 0.5 kg / cm ²	60
----------------------	---------------	-----------	------------	-----------------------------------	----

Scroll down for other FR-products.

Ready FR emblems (up to 95 °C laundry wash)			
Type of fabric	Temp. °C	Pressing time in sec.	Pressure in Bar Low/Medium/High
Fleece, 100% Polyester	-	-	-

Polyurethane or PVC coated polyester (rainwear), cover with baking paper	-	-	-
Knitted fabrics, 100% polyester, viscose, acrylic (Sportswear, light workwear)	-	-	-
Knitted fabrics, 100% wool, cotton (Sportswear, light workwear)	185 - 195	15	4-5 (Medium/High)
Knitted fabrics, cotton or polyester with elastane 98%/2%	-	-	-
Flame-retardant cotton or polyester cotton (FR treated, Proban®)	185 - 195	15	4-6 (Medium/High)
Cotton/polyamide 55%/45%	Preheat 195	10 15	4-6 (Medium/High)
Cotton/polyester 65%/35% or 60%/40% (with DWR finish)*	195	15	4-6 (Medium/High)
Aramid/Viscose 50%/50%	185	15	4-6 (Medium/High)
Linen, 100%	195	15	4-6 (Medium/High)
Aramid (Nomex III), 100%	185	15	4-6 (Medium/High)
Polyamide (Nylon), 100% (with DWR finish)*	185	15	4-6 (Medium/High)
Polyester 100% (with DWR finish)*	185	15	4-6 (Medium/High)
Polyester Cleanroom material anti-static 99%/1%	-	-	-

ReadyPly FR emblems (up to 95 °C laundry wash)			
Type of fabric	Temp. °C	Pressing time in sec.	Pressure in Bar Low/Medium/High
Fleece, 100% Polyester	-	-	-
Polyurethane or PVC coated polyester (rainwear), cover with baking paper	-	-	-
Knitted fabrics, 100% polyester, viscose, acrylic (Sportswear, light workwear)	-	-	-
Knitted fabrics, 100% wool, cotton (Sportswear, light workwear)	185 - 195	15	4-5 (Medium/High)
Knitted fabrics, cotton or polyester with elastane 98%/2%	-	-	-
Flame-retardant cotton or polyester cotton (FR treated, Proban®)	185 - 195	15	4-6 (Medium/High)
Cotton/polyamide 55%/45%	Preheat 195	10 15	4-6 (Medium/High)
Cotton/polyester 65%/35% or 60%/40% (with DWR finish)*	195	15	4-6 (Medium/High)
Aramid/Viscose 50%/50%	185	15	4-6 (Medium/High)
Linen, 100%	195	15	4-6 (Medium/High)
Aramid (Nomex III), 100%	185	15	4-6 (Medium/High)

Polyamide (Nylon), 100% (with DWR finish)*	-	-	-
Polyester 100% (with DWR finish)*	-	-	-
Polyester Cleanroom material anti-static 99%/1%	-	-	-

**DWR finish: Durable Water Repellent finish, meaning a water (dirt, oil) repellent coating on textiles based on silicone, nanotechnology, wax, and fluorocarbon.*

FR: Flame Retardant

Disclaimer

No rights can be derived from the instructions or data provided online. The information is intended for general guidance only and is subject to change without notice. We do not guarantee the accuracy, completeness, or reliability of the information provided. Users are advised to verify any information before acting on it. We accept no liability for any damage incurred because of relying on this information.